



Technical Data Sheet

www.pamfast.com



**Modify Wafer Head with 8 Nibs, PAMDrive Recess,
Coarse Thread, Sharp Point,
Magni 599 Coating, W-72 (2,000 Hour Salt Spray Test)
MWMC8114**

Head Diameter	8.80 – 9.30 mm
Major Diameter	4.05 – 4.35 mm
Min. Diameter	2.70-2.90 mm
Length	31.75 ±.8 mm
Access Depth	1.65 – 2.08 mm
Wire Diameter	3.15 mm
Surface Hardness	550-750 HV
Core Hardness	450 – 240 HV
Breaking Torque	min. 42 (KG/CM)
Penetration	1”
Withdrawal	830 lbs
Material	C1022
Salt Spray Test (ASTM B-117)	2000 Hours
Bent Testing	15°

All fasteners manufactured for PAM Fastening Technology, Inc. are of a non-chemical hazardous nature.

Important Notice: The details in our sheets and other PAM publications are provided to the best of our knowledge. The contents, however, are not legally binding. In all cases we recommend that preliminary tests be carried out by the customer. In all respects our general terms of sale shall apply.

PAM[®]

PAM Fastening Technology, Inc.

2120 Gateway Blvd. • Charlotte, NC 28208

704/394-3141 • Fax 704/394-9339 • email: sales@pamfast.com