

Technical Data Sheet

www.pamfast.com



**Flat Head, PAMDrive, 2/3 Coarse Thread (8 T.P.I.)
Sharp Point, Hardened, Copperhead Coating, 1000 Hour Salt
Spray
WTDC8300, #8 x 3"
PAM Fastening Technology, Inc.**

Head Diameter	8.00 – 8.50 mm
Major Diameter	4.30 – 4.70 mm
Min. Diameter	3.80 – 4.00 mm
Length	76.2 ± 1.0 mm
Access Depth	1.65 – 2.08 mm
Wire Diameter	3.30 mm
Surface Hardness	450 – 700 (HV)
Core Hardness	
Breaking Torque	Min 45 (KG – CM)
Penetration	1"
Withdrawal	950 lbs
Material	C 1022
Salt Spray Test	1000 Hours per ASTM G-85 test
Bent Testing	15°

All fasteners manufactured for PAM Fastening Technology, Inc. are of a non-chemical hazardous nature.

Important Notice: The details in our sheets and other PAM publications are provided to the best of our knowledge. The contents, however, are not legally binding. In all cases we recommend that preliminary tests be carried out by the customer. In all respects our general terms of sale shall apply.

PAM[®]

PAM Fastening Technology, Inc.

2120 Gateway Blvd. • Charlotte, NC 28208

704/394-3141 • Fax 704/394-9339 • email: sales@pamfast.com